



STRahl & PITsch

230 Great East Neck Rd., West Babylon, NY 11704, U.S.A.

Phone: 631.587.9000 Fax: 631.587.9120

www.spwax.com

Synthetic Beeswax

SP-772

SP-772P



Test	Method	Specification
Color	Visual	Off White
Melting Point	Current NF monograph	62.0 – 65.0 °C
Penetration	ASTM D-1321	8 - 14
Acid Value	Current NF monograph	17 - 24
Saponification Value	Current NF monograph	89 - 103


7/2/09

Signature **Date**

Version: A
Supersedes: None